

Intertherm 228

Epoxy Phenolic



Product Description

A highly crosslinked, two component, high build Epoxy Phenolic coating which combines properties of corrosion and chemical resistance when used in high temperature service.

Intended Uses

Intertherm 228 has been specifically designed to provide a corrosion resistant barrier when used to protect steelwork beneath thermal insulation in areas subjected to wet and dry cycling.

Suitable for exposure in a wide range of highly corrosive environments, including insulated and uninsulated steel, and on the exterior or pipework, process vessels etc., operating at temperatures up to 230°C (446°F).

Intertherm 228 has excellent resistance to "thermal shock" experienced during rapid temperature cycling.

Practical Information for Intertherm 228

Colour	Limited Range
Gloss Level	Eggshell
Volume Solids	67%
Typical Thickness	100 microns (4 mils) dry equivalent to 149 microns (6.0 mils) wet
Theoretical Coverage	6.7 m ² /litre @ 100 microns d.f.t. and stated volume solids 269 sq.ft./US gallon @ 4 mils d.f.t. and stated volume solids
Practical Coverage	Allow appropriate loss factors
Method of Application	Airless spray, Airspray, Brush, Roller
Drying Time	

Temperature	Touch Dry	Hard Dry	Overcoating Interval Intertherm 228 with self	
			<i>Minimum</i>	<i>Maximum</i>
10°C (50°F)	8 hours	16 hours	36 hours	5 days
15°C (59°F)	7 hours	12 hours	24 hours	4 days
25°C (77°F)	5 hours	8 hours	16 hours	3 days
40°C (104°F)	3 hours	6 hours	16 hours	2 days

Regulatory Data

Flash Point	Base (Part A) 26°C (79°F)	C/A (Part B) 48°C (118°F)	Mixed 24°C (75°F)
Product Weight	1.85kg/l (15.5lb/gal)		
VOC	270g/l (2.25lb/gal) 2.83lb/gal (340g/l)	UK - PG6/23(92), Appendix 3 USA - EPA Method 24	



Ecotech is an initiative by International Protective Coatings a world leader in coating technology to promote the use of environmentally sensitive products across the globe.

Intertherm 228

Epoxy Phenolic

Surface Preparation

All surfaces to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:1992.

Where necessary, remove weld spatter, and where required smooth weld seams and sharp edges.

Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Abrasive Blast Cleaning

This product must only be applied to surfaces prepared by abrasive blast cleaning to a minimum Sa2½ (ISO 8501-1:1988) or SSPC SP6.

A sharp, angular surface profile of 50-75microns (2-3 mils) is recommended.

Intertherm 228 must be applied before oxidation of the steel occurs. If oxidation does occur the entire oxidised area should be reblasted to the standard specified above.

Surface defects revealed by the blast cleaning process, should be ground, filled, or treated in the appropriate manner.

Surfaces may be primed with Intertherm 228 (thinned 10% GTA220) to 40 microns (1.5 mils) dry film thickness before oxidation occurs.

Power Tool Cleaning (Small Areas Only)

Intertherm 228 is suitable for application over power tool cleaned surfaces prepared to a minimum of SSPC SP11.

Note, all scale must be removed and all areas which cannot be prepared adequately should be spot blasted to a minimum standard of Sa2 (ISO 8501-1:1988) or SSPC SP6.

Application

Mixing	Material is supplied in two containers as a unit. Always mix a complete unit in the proportions supplied. Once the unit has been mixed it must be used within the working pot life specified.			
	<ol style="list-style-type: none"> (1) Agitate Base (Part A) with a power agitator. (2) Agitate Curing Agent (Part B) with a power agitator. (3) Combine entire contents of Curing Agent (Part B) with Base (Part A) and mix thoroughly with power agitator. 			
Mix Ratio	5 parts : 1 parts by volume.			
Working Pot Life	10°C (50°F) 5 hours	15°C (59°F) 4 hours	25°C (77°F) 2 hours	40°C (104°F) 1 hour
Airless Spray	Recommended	-- Tip range 0.43-0.53mm (17-21 thou) Total output fluid pressure at spray tip not less than 176kg/cm ² (2,500 p.s.i.)		
Air Spray (Pressure Pot)	Recommended	Gun Air Cap Fluid Tip	DeVilbiss MBC or JGA 704 or 765 E	
Brush	Suitable - Small areas only	Typically 50-75 microns (2-3 mils) can be achieved		
Roller	Suitable - Small areas only	Typically 50-75 microns (2-3 mils) can be achieved		
Thinner	International GTA220 (or GTA415)	Do not thin more than allowed by local environmental legislation.		
Cleaner	International GTA822 (or GTA415)			
Work Stoppages	Do not allow material to remain in hoses, gun or spray equipment. Thoroughly flush all equipment with International GTA822. Once units of paint have been mixed they should not be resealed and it is advised that after prolonged stoppages work recommence with freshly mixed units.			
Clean Up	Clean all equipment immediately after use with International GTA822. It is good working practice to periodically flush out spray equipment during the course of the working day. Frequency of cleaning will depend upon amount sprayed, temperature and elapsed time, including any delays.			
	All surplus materials and empty containers should be disposed of in accordance with appropriate regional regulations/legislation.			

Intertherm 228

Epoxy Phenolic

Product Characteristics

Intertherm 228 is typically applied as a two coat system at 100 microns (4 mils) per coat to give a total coating system dry film thickness of 200 microns (8 mils).

Maximum film build in one coat is best attained by airless spray. When applying by methods other than airless spray, the required film build is unlikely to be achieved. Application by air spray may require a multiple cross spray pattern to attain optimum film build. The use of other methods, e.g. brush or roller, may require more than one coat and are suggested only for small areas, or initial stripe coating.

When applying Intertherm 228 by brush or roller, it may be necessary to apply multiple coats to achieve the total specified system dry film thickness.

If Intertherm 228 is to be applied by brush to coat small areas for maintenance purposes, it is recommended that Intertherm 228 is applied as a three coat system at 65 microns (2.5 mils) per coat to give a total coating system dry film thickness of 195 microns (7.5 mils).

Surface temperature must always be a minimum of 3°C (5°F) above dew point.

Do not apply at steel temperatures below 10°C (50°F).

The relative humidity during application and curing should not exceed 80%.

Good ventilation throughout application and cure, and firm control of film thickness, are essential to ensure full removal of retained solvent and optimum performance of cured film. Care should be taken to avoid over-application. The total coating system film thickness applied must not exceed 300 microns (12 mils) in order to avoid cracking during high temperature service.

When applying Intertherm 228 in confined spaces ensure adequate ventilation.

After the last coat has cured hard, the coating system dry film thickness should be measured using a suitable non-destructive magnetic gauge to verify the average total applied system thickness. The coating system should be free of all pinholes or other holidays. The cured film should be essentially free of runs, sags, drips, inclusions or other defects. All deficiencies and defects should be corrected.

The curing times will vary depending upon dry film thickness and conditions that exist during application and throughout curing periods.

Maximum performance is not attained until the film has completely cured. Cure is a function of temperature, humidity and film thickness. Normally Intertherm 228 coating systems at 200 microns (8 mils) dry film thickness will exhibit full and complete cure for optimal temperature resistance in 7-10 days at 25°C (77°F). Curing times are proportionately shorter at elevated temperatures and longer at lower temperatures.

In common with all epoxies Intertherm 228 will chalk and "yellow" on exterior exposure. Intertherm 228 will also show a marked colour change when exposed to higher temperatures. This colour change is more noticeable in lighter shades and at temperatures in excess of 150°C (302°F). However, these phenomena are not detrimental to anti-corrosive performance provided recommended temperature limits are not exceeded.

Intertherm 228 is suitable for protection of insulated steelwork, which may cycle between wet and dry conditions, and is operating at continuous in-service temperatures ranging from ambient up to 200°C (392°F), with intermittent surges up to 230°C (446°F).

Intertherm 228 is an immersion grade epoxy phenolic coating, and is suitable for use in situations of continuous intimate contact with wet insulation. However, Intertherm 228 is not intended for use as an internal tanklining

Systems Compatibility

This system is self-priming and is not suitable for application over other primers. Intertherm 228 is normally topcoated with itself, for other suitable topcoats please consult International Protective Coatings.

Intertherm 228

Epoxy Phenolic

Additional Information

Further information regarding industry standards, terms and abbreviations used in this data sheet can be found in the following sections of the International Protective Coatings data manual:

- Definitions & Abbreviations
- Surface Preparation
- Paint Application
- Theoretical & Practical Coverage

Individual copies of these information sections are available upon request.

Safety Precautions

This product is intended for use only by professional applicators in industrial situations in accordance with the advice given on this sheet, the Material Safety Data Sheet and the container(s), and should not be used without reference to the Material Safety Data Sheet (MSDS) which International Protective Coatings has provided to its customers.

All work involving the application and use of this product should be performed in compliance with all relevant national, Health, Safety & Environmental standards and regulations.

In the event welding or flame cutting is performed on metal coated with this product, dust and fumes will be emitted which will require the use of appropriate personal protective equipment and adequate local exhaust ventilation.

If in doubt regarding the suitability of use of this product, consult International Protective Coatings for further advice.

Pack Size	20 litre unit	Intertherm 228 Base	16.67 litres in a 20 litre container
		Intertherm 228 Curing Agent	3.33 litres in a 5 litre container
	5 gallon unit	Intertherm 228 Base	4.167 gallons in a 5 gallon container
		Intertherm 228 Curing Agent	0.833 gallons in a 1 gallon container
For availability of other pack sizes contact International Protective Coatings			
Shipping Weight	U.N. Shipping No. 1263		
	20 litre unit	35.7kg (78.7lbs) Base (Part A)	3.96kg (8.7lbs) Curing Agent (Part B)
	5 gallon unit	72.96lbs (33.1kg) Base (Part A)	8.03lbs (3.64kg) Curing Agent (Part B)
Storage	Shelf Life	12 months minimum at 25°C (77°F). Subject to re-inspection thereafter. Store in dry, shaded conditions away from sources of heat and ignition.	

Disclaimer

The information given in this sheet is not intended to be exhaustive and any person using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. Any warranty, if given, or specific Terms & Conditions of Sale are contained in International's Terms & Conditions of Sale, a copy of which can be obtained on request. Whilst we endeavour to ensure that all advice we give about the product (whether in this sheet or otherwise) is correct we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage (other than death or personal injury resulting from our negligence) arising out of the use of the product. The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development. It is the user's responsibility to check that this sheet is current prior to using the product. Issue date: 19/06/2002

Copyright © International Paint Ltd. and International are trademarks.

International Protective Coatings

Worldwide Availability

World Centre	Asia Region	Australasia Region	Europe Region	Middle East Region	North America Region	South America Region
P.O Box 20980 Oriol House 16 Connaught Place London, W2 2ZB England	3 Neythal Road Jurong Town Singapore 628570	115 Hyde Road Yeronga Brisbane Queensland Australia	P.O Box 20980 Oriol House 16 Connaught Place London, W2 2ZB England	PO Box 37 Dammam 31411 Saudi Arabia	6001 Antoine Drive Houston Texas 77091	Av Paiva 999, Neves, Sao Gonçalo, Rio de Janeiro Brazil

Tel: (44) 20 7479 6000	Tel: (65) 663 3066	Tel: (61) 7 3892 8888	Tel: (44) 20 7479 6000	Tel: (966) 3 812 1044	Tel: (1) 713 682 1711	Tel: (55) 21 624 7100
Fax: (44) 20 7479 6500	Fax: (65) 266 5287	Fax: (61) 7 3892 4287 H&S (61) 1800 807 001	Fax: (44) 20 7479 6500	Fax: (966) 3 812 1169	Fax: (1) 713 684 1514	Fax: (55) 21 624 7123